

# Hendy Coils Pty Ltd

## PROTECTIVE ACRYLIC METACRYLATE COATING

### TECHNICAL SPECIFICATIONS

Composition:	Clear solvent - borne acrylic																						
Color:	Transparent Red																						
Typical Application:	Coils that require protection from corrosive agents: - Examples - Swimming pool areas - Areas near salt spray																						
Weathering:	Excellent Resistance to U.V. Light																						
Chemical Resistance:	<table><thead><tr><th><u>Chemical</u></th><th><u>Resistance</u></th></tr></thead><tbody><tr><td>Chlorine vapor</td><td>Excellent</td></tr><tr><td>Salt spray</td><td>Excellent</td></tr><tr><td>Acetic acid</td><td>Excellent</td></tr><tr><td>Ammonia</td><td>Excellent</td></tr><tr><td>Hydrochloric acid</td><td>Good</td></tr><tr><td>Sulphuric acid</td><td>Good</td></tr><tr><td>Nitric acid</td><td>Good</td></tr><tr><td>Acetone</td><td>Poor</td></tr><tr><td>Methylated spirits</td><td>Poor</td></tr><tr><td>Toluene</td><td>Poor</td></tr></tbody></table>	<u>Chemical</u>	<u>Resistance</u>	Chlorine vapor	Excellent	Salt spray	Excellent	Acetic acid	Excellent	Ammonia	Excellent	Hydrochloric acid	Good	Sulphuric acid	Good	Nitric acid	Good	Acetone	Poor	Methylated spirits	Poor	Toluene	Poor
<u>Chemical</u>	<u>Resistance</u>																						
Chlorine vapor	Excellent																						
Salt spray	Excellent																						
Acetic acid	Excellent																						
Ammonia	Excellent																						
Hydrochloric acid	Good																						
Sulphuric acid	Good																						
Nitric acid	Good																						
Acetone	Poor																						
Methylated spirits	Poor																						
Toluene	Poor																						
Abrasion Resistance:	Good																						
Typical Coverage:	Approx. 15 microns																						
Feature:	Does not impare heat transfer																						
Hazchem code:	3 (y) E																						
Ingredients:	<table><thead><tr><th><u>Chemical</u></th><th><u>Proportion</u></th></tr></thead><tbody><tr><td>Methyl iso butyl ketone</td><td>30 - 60 %</td></tr><tr><td>Toluene</td><td>10 - 30 %</td></tr><tr><td>Xylene</td><td>10 - 30 %</td></tr><tr><td>Resins</td><td>10 - 30 %</td></tr><tr><td>Other</td><td>&lt; 1 %</td></tr></tbody></table>	<u>Chemical</u>	<u>Proportion</u>	Methyl iso butyl ketone	30 - 60 %	Toluene	10 - 30 %	Xylene	10 - 30 %	Resins	10 - 30 %	Other	< 1 %										
<u>Chemical</u>	<u>Proportion</u>																						
Methyl iso butyl ketone	30 - 60 %																						
Toluene	10 - 30 %																						
Xylene	10 - 30 %																						
Resins	10 - 30 %																						
Other	< 1 %																						